



COATING PRODUCTS: Technical Data Sheet

PRODUCT: ALKYDS Resyd 2113 Z 60

RESYD 2113 Z 60 is a medium oil alkyd, thinned in tertiary butyl acetate. Designed specifically for traffic paints that require a VOC exempt solvent.

APPLICATIONS:

- Traffic Paints (VOC exempt)

FEATURES:

- Fast time to no pick-up
- Excellent pigment compatibility
- Good durability

TYPICAL PHYSICAL PROPERTIES:

PERCENT SOLIDS	59.0 – 61.0
SOLVENT	<i>t</i> Butyl Acetate
ACID VALUE (SOLIDS)	25 max.
COLOR, GARDNER	2 - 6
VISCOSITY @ 25 ⁰ C. (GARDNER HOLDT)	Z-Z ₂
% PHTHALIC ANHYDRIDE (ON SOLIDS)	35 min.
% OIL (ON SOLIDS) CALCULATED	51
SPECIFIC GRAVITY – SOLUTION (AVG.)	1.01
SPECIFIC GRAVITY – POLYMER (AVG.)	1.15

RECOMMENDED STORAGE:

Store in a cool, dry place, preferably under 25 °C to ensure a useful shelf life of at least one year. Read the RESYD 2113 Z 60 material safety data sheet before handling, storing or using this material.

RESYD 2113 Z 60 is available in steel drums or bulk tanker.

Ref. # EP-1113-A

BEFORE USE, ALWAYS READ AND FOLLOW THE DIRECTIONS CONTAINED ON THE LABEL, AND MATERIAL SAFETY DATA SHEET.

** The information presented, while not guaranteed, it is to the best of our knowledge true and accurate. No warranty or guarantee, express or implied, is made regarding the performance or stability of any product, since the manner of use and conditions of storage and handling are beyond our control. No suggestions for product use are intended as and nothing herein shall be construed as a recommendation to infringe any existing patents or to violate any government laws.



MANCUSO CHEMICALS LIMITED
5725 Progress St.
Niagara Falls, Ont.
Canada L2G 0C1
www.mancusochemicals.com

MTDS Resyd 2113 Z 60 v1 September 11, 2012



FOUNDRY – COATINGS – STEEL MILL - SULPHONIC ACIDS - PSA
TOMORROW'S GREEN CHEMISTRY, TODAY