



## COATING PRODUCTS: Technical Data Sheet

### ALKYD RESIN

**RESYD 2204 x 60** is a fast dry medium oil linseed alkyd meeting MIL-P-8585A and MIL-P-7926B vehicle requirements. It has excellent wetting and adhesion.

#### TYPICAL PHYSICAL PROPERTIES\*:

PERCENT SOLIDS	60.0 ± 1.0
SOLVENT	Xylene
ACID VALUE	15 max. on solution
MODIFIERS	None
COLOR	9 max.
VISCOSITY	Z <sub>2</sub> – Z <sub>3</sub>
PHTHALIC ANHYDRIDE (ON RESIN)	38 % Approx.
TYPE OF OIL	Linseed
SPECIFIC GRAVITY – SOLUTION	1.01
SPECIFIC GRAVITY – SOLIDS	1.19
REDUCED VISCOSITY @ 50%	G – I in Xylene

**RESYD 2204 x 60** is available in steel drums or bulk tanker.  
Ref.# EP-204-A

BEFORE USE, ALWAYS READ AND FOLLOW THE DIRECTIONS CONTAINED ON THE LABEL, AND MATERIAL SAFETY DATA SHEET.

\*\* The information presented, while not guaranteed, it is to the best of our knowledge true and accurate. No warranty or guarantee, express or implied, is made regarding the performance or stability of any product, since the manner of use and conditions of storage and handling are beyond our control. No suggestions for product use are intended as and nothing herein shall be construed as a recommendation to infringe any existing patents or to violate any government laws.

Technical Data



**MANCUSO CHEMICALS LIMITED**  
5725 Progress St.  
Niagara Falls, Ont.  
Canada L2G 0C1  
[www.mancusochemicals.com](http://www.mancusochemicals.com)

MTDS Resyd 2204 X 60 v3 January 22, 2013



FOUNDRY – COATINGS – STEEL MILL - SULPHONIC ACIDS - PSA  
TOMORROW'S **GREEN** CHEMISTRY, TODAY