



## COATING PRODUCTS: Technical Data Sheet

### ALKYD RESIN

**RESYD 3630 Z 70** is a short, fast drying Tall Oil Alkyd. A general purpose air dry, forced air dry and baking resin that is fully suited to drum enamels, tool and garden machinery applications as well as general interior and exterior applications:

- Low VOC product
- Very fast drying times with standard dryers
- Isocyanate reactive for MAR resistant coatings
- Compatible with fully and partially methylated melamines
- With mixed ether crosslinking, will provide exceptional flow, leveling and gloss in low VOC bake applications

#### TYPICAL PHYSICAL PROPERTIES\*:

PERCENT SOLIDS	69.0 – 71.0
SOLVENT	Xylene/Glycol Ether PM Acetate
ACID VALUE	14 max.
PHENOLIC CONTENT	None
COLOR	6 max.
VISCOSITY	Z <sub>1</sub> – Z <sub>3</sub> <sup>+</sup>
REDUCED VISCOSITY @ 50% NV	C - F
SPECIFIC GRAVITY	Appr. 1.01 Kg/L (3.82 Kg/USG or 8.42 lbs/USG)

**RESYD 3630 Z 70** is available in steel drums or bulk tanker.

Ref.# EP-630-A

BEFORE USE, ALWAYS READ AND FOLLOW THE DIRECTIONS CONTAINED ON THE LABEL, AND MATERIAL SAFETY DATA SHEET.

\*\* The information presented, while not guaranteed, it is to the best of our knowledge true and accurate. No warranty or guarantee, express or implied, is made regarding the performance or stability of any product, since the manner of use and conditions of storage and handling are beyond our control. No suggestions for product use are intended as and nothing herein shall be construed as a recommendation to infringe any existing patents or to violate any government laws.



**MANCUSO CHEMICALS LIMITED**  
5725 Progress St.  
Niagara Falls, Ont.  
Canada L2G 0C1  
[www.mancusochemicals.com](http://www.mancusochemicals.com)

MTDS Resyd 3630 Z 70 v3 January 22, 2013



FOUNDRY – COATINGS – STEEL MILL - SULPHONIC ACIDS - PSA  
TOMORROW'S GREEN CHEMISTRY, TODAY