



COATING PRODUCTS: Technical Data Sheet

PRODUCT: ALKYDS Resyd 5111 Z 60

RESYD 5111 Z 60 is a short oil soya alkyd, thinned in tertiary butyl acetate. Designed specifically for traffic paints that require a VOC exempt solvent.

APPLICATIONS:

- Traffic Paints (VOC exempt)

FEATURES:

- Fast time to no pick-up
- Good hardness
- Good durability

TYPICAL PHYSICAL PROPERTIES:

PERCENT SOLIDS	59.0 – 61.0
SOLVENT	tButyl Acetate
ACID VALUE (SOLIDS)	14 max.
COLOR, GARDNER	2 - 6
VISCOSITY @ 25 ⁰ C. (GARDNER HOLDT)	Z ₂ -Z ₄
% PHTHALIC ANHYDRIDE (ON SOLIDS)	42 min.
% OIL (ON SOLIDS) CALCULATED	36
SPECIFIC GRAVITY – SOLUTION (AVG.)	1.01
SPECIFIC GRAVITY – POLYMER (AVG.)	1.155

RECOMMENDED STORAGE:

Store in a cool, dry place, preferably under 27 °C to ensure a useful shelf life of at least one year. Read the RESYD 5111 Z 60 material safety data sheet before handling, storing or using this material.

RESYD 5111 Z 60 is available in steel drums or bulk tanker.

Ref. # EP-1111-A

BEFORE USE, ALWAYS READ AND FOLLOW THE DIRECTIONS CONTAINED ON THE LABEL, AND MATERIAL SAFETY DATA SHEET.

** The information presented, while not guaranteed, it is to the best of our knowledge true and accurate. No warranty or guarantee, express or implied, is made regarding the performance or stability of any product, since the manner of use and conditions of storage and handling are beyond our control. No suggestions for product use are intended as and nothing herein shall be construed as a recommendation to infringe any existing patents or to violate any government laws.



MANCUSO CHEMICALS LIMITED
5725 Progress St.
Niagara Falls, Ont.
Canada L2G 0C1
www.mancusochemicals.com



MTDS Resyd 5111 Z 60 v1 September 11, 2012

FOUNDRY – COATINGS – STEEL MILL - SULPHONIC ACIDS - PSA
TOMORROW'S GREEN CHEMISTRY, TODAY